

# polarized 167/32

## aspheric blank data sheet

A remarkably thin step closer to natural sight

**ASAHI-LITE**<sup>®</sup>  
A MEMBER OF THE ONO GROUP

diameter (mm)	nominal convex curve (D)	power range at main meridian (D)	actual convex curve (N = 1,530) (D)	radius of curvature (mm)	sagitta depth gauge 50 mm bell (mm)	nominal concave curve (N = 1,530) (D)	polarizing film curve (D)/N = 1,530	center thickness (mm)	edge thickness (mm)
70	0,50	-6.25 to -10.00	0,63	837,38	0,37	3,47	3,60	11,0	14,0
75	2,00	-3.25 to -6.00	2,23	237,88	1,32	4,35	3,60	9,4	12,0
75	4,00	±0.00 to -3.00	3,73	141,90	2,22	5,73	3,60	10,0	11,0
75	6,00	+0.25 to +3.00	5,72	92,69	3,44	4,35	5,53	9,2	8,0
75	8,00	+3.25 to +8.00	8,22	64,50	5,04	6,31	8,15	10,1	8,0

color density	polarization
85 % Grey	99 %
85 % Brown	97 %
70 % Light Grey	94 %
70 % Light Brown	93 %